

AÇOS GLOBOLTDA
DESDE 1978



AÇOS GLOBOLTDA
Telefone(Pabx):112024.7500-Fax:112918.8899
RuaSusana,254-JdIndependência-(VilaPrudente)
E-mail:agl@acosglobo.com.br-E-mail:acosglobo@ig.com.br
SãoPaulo-SP-Brasil-SiteByOesp

CHAPAS FINAS A QUENTE

Bitola GSG	Espessura mm	Peso Kg / m ²
3,16	4,76	37,348
7	4,55	36,618
8	4,18	33,566
9	3,8	30,515
10	3,42	27,464
11	3,04	24,412
12	2,66	21,36
13	2,28	18,309
14	1,9	15,258
15	1,71	13,732
16	1,52	12,206